

FIBREGLASS & FOAMS

Diggers Fibreglass Resin Catalyst

DESCRIPTION

Diggers Fibreglass Resin Catalyst is the hardener required to set off Diggers Fibreglass Resin and Diggers Casting and Embedding Resin.

TYPICAL USES

- Curing polyester resins

FEATURES

- A colourless liquid with a mildly pungent odour
- Easy-to-use dropper bottle for more accurate measurement

APPLICATION

1. Mix resin with catalyst: for 100ml of resin (cold day) use 2.5 to 3ml catalyst; and for 100ml resin (hot day) use 1.5 to 2ml catalyst.
2. Use a measuring cup for the amount of catalyst needed or if using the dropper bottle 1ml = 45 drops. Mix the catalyst into the resin using a flat stirring stick until a uniform colour has been achieved.
3. Make allowances for temperature, humidity, depth of resin and draughts as these factors can affect the amount of catalyst needed.

SAFETY

Wear suitable protective clothing, gloves and eye / face protection when using this product.

Typical Characteristics

Appearance.....colourless
clear liquid
Odour.....faint
Specific Gravity..... 1.18
Flash Point.....68°C
Freezing Point.....-10°C



MSDS available



Code	Pack Size	Unit Barcode	Carton Barcode	Ctn/Pit
FIRC01506	6 x 15ml	9312852002448	19312852002285	6 / tray
FIRC120	1 x 120ml	9311052000735	N/A	N/A

QUEENSLAND
Tel +61 7 3308 5200
Fax +61 7 3308 5201

NEW SOUTH WALES
Tel +61 2 8709 9600
Fax +61 2 9791 5066

VICTORIA
Tel +61 3 9408 4144
Fax +61 3 9408 4155

SOUTH AUSTRALIA
Tel +61 8 8222 1333
Fax +61 8 8260 7883

WESTERN AUSTRALIA
Tel +61 8 9352 3000
Fax +61 8 9352 3033

© Copyright Recochem Inc. All rights reserved. All content remains the property of Recochem Inc. All other trademarks mentioned are trademarks or registered trademarks of their respective owners. All text, images, graphics and PDF files are subject to the copyrights and intellectual property rights of Recochem Inc. Separate to the purpose of review and private use, this information cannot be used without written permission from Recochem. Information contained herein is for general information only and should not be used as an infallible to a product's specification and or performance.