

OXIDES & POWDERS

Diggers Plaster of Paris

DESCRIPTION

Diggers Plaster of Paris is a fast setting casting plaster commonly used for modelling and repairs to ceilings and walls. Unlike mortar and cement, **Diggers Plaster of Paris** remains comparatively soft after drying.

TYPICAL USES

- Grouting
- Repairs
- Casting
- Modelling

FEATURES

- Quick-setting - sets hard in 20 to 30 minutes
- Minimal shrinkage during setting as it hardens externally before water leeches or evaporates
- Will expand slightly upon setting giving a fine detailed cast
- Once coated with **Diggers Raincoat** the end product will be protected from moisture that might soften the plaster when placed outdoors
- Can be coloured with **Diggers Oxide**

APPLICATION

1. Ensure all utensils are clean.
2. Add 1 part water to 2 parts **Diggers Plaster of Paris** and stir the mix to a creamy consistency.
3. If a colour is required, **Diggers Oxide** can be added to the mix. Mixture will set in approximately 15 minutes.

SAFETY

Wear suitable protective clothing, gloves and eye / face protection when using this product.

Typical Characteristics

Appearance fine powder
 Odour no distinctive odour
 Specific Gravity 2.5–3.5
 Melting Point 163°C

 **MSDS** available



Code	Pack Size	Unit Barcode	Carton Barcode	Ctn/Plt
PLP0105	5 x 1kg	9311052002388	19312852003138	185
PLP0305	5 x 3kg	9311052002395	19312852003145	80

QUEENSLAND
Tel +61 7 3308 5200
Fax +61 7 3308 5201

NEW SOUTH WALES
Tel +61 2 8709 9600
Fax +61 2 9791 5066

VICTORIA
Tel +61 3 9408 4144
Fax +61 3 9408 4155

SOUTH AUSTRALIA
Tel +61 8 8222 1333
Fax +61 8 8260 7883

WESTERN AUSTRALIA
Tel +61 8 9352 3000
Fax +61 8 9352 3033

© Copyright Recochem Inc. All rights reserved. All content remains the property of Recochem Inc. All other trademarks mentioned are trademarks or registered trademarks of their respective owners. All text, images, graphics and PDF files are subject to the copyrights and intellectual property rights of Recochem Inc. Separate to the purpose of review and private use, this information cannot be used without written permission from Recochem. Information contained herein is for general information only and should not be used as an infallible to a product's specification and or performance.